

GPI[®] Series I-Joists
Georgia-Pacific Wood Products South LLC

PR-L276
Revised August 15, 2011

Products: GPI[®] 40, 65 and 90 Series I-Joists
Georgia-Pacific Wood Products South LLC, 19953 Highway 31, Thorsby, Alabama 35171
(205) 646-3346
www.gp.com/build/

1. Basis of the product report:
 - 2009 and 2006 International Building Code (IBC): Sections 104.11 Alternative Materials and 2303.1.2 Prefabricated wood I-joists
 - 2009 and 2006 International Residential Code (IRC): Sections R104.11 Alternative Materials and R502.1.4 Prefabricated wood I-joists
 - ASTM D5055-05 and D5055-04 recognized by the 2009 IBC and IRC, and 2006 IBC and IRC, respectively
 - APA Reports T2001P-21, T2001P-84, T2003P-62, T2003P-70, T2007P-54, T2007P-83, and T2008P-48, T2010P-12, T2010P-34, and other qualification data.
2. Product description:

GPI[®] 40, 65 and 90 Series I-joists are made with laminated veneer lumber (LVL) flanges and OSB webs in accordance with the in-plant manufacturing standard approved by APA.
3. Design properties:

Table 1 lists the design properties for GPI[®] 40, 65 and 90 Series I-joists. The allowable spans for GPI[®] Series I-joists covered by this report shall be in accordance with the recommendations provided by the manufacturer (www.gp.com/build/product.aspx?pid=1390).
4. Product installation:

GPI[®] 40, 65 and 90 Series I-joists covered by this report shall be installed in accordance with the recommendations provided by the manufacturer (see link above). Permissible web holes and cantilever reinforcements shall be in accordance with the recommendations provided by the manufacturer.
5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above), and with APA Design/Construction Guide: *Fire-Rated Systems*, Form W305 (www.apawood.org/publications).
6. Limitations:
 - a) GPI[®] 40, 65 and 90 Series I-joists shall be designed in accordance with the code using the design properties specified in this report.
 - b) GPI[®] 40, 65 and 90 Series I-joists are limited to dry service conditions where the average equilibrium moisture content of sawn lumber is less than 16 percent.
 - c) GPI[®] 40, 65 and 90 Series I-joists are produced at the Georgia-Pacific Wood Products South LLC, Thorsby, Alabama facilities under a quality assurance program audited by APA.
 - d) This report is subject to re-examination in one year.
7. Identification:

The GPI[®] Series I-joists described in this report are identified by a label bearing the manufacturer's name (Georgia-Pacific Wood Products South LLC) and/or trademark,

the APA assigned plant number (1085), the I-joist depth and series, the APA logo, the report number PR-L276, and a means of identifying the date of manufacture.

Table 1. Design Properties (Allowable Stress Design) for GPI® Series I-joists ^(a,b)

Joist Depth (in.)	Joist Series	Corresponding PRI Series	EI ^(c) (x10 ⁶ lbf-in. ²)	M ^(d) (lbf-ft)	V ^(e) (lbf)	End Reaction ^(f) (lbf)				Intermediate Reaction (lbf)				C ^(g) (x10 ⁶ ft-lb/in.)
						1-3/4 in. Brg. Length		4 in. Brg. Length		3-1/2 in. Brg. Length		5-1/4 in. Brg. Length		
						w/o Brg. Stiff	w/Brg. Stiff	w/o Brg. Stiff	w/Brg. Stiff	w/o Brg. Stiff	w/Brg. Stiff	w/o Brg. Stiff	w/Brg. Stiff	
9-1/2	GPI 40	PRI-40	193	3,090	1,200	1,120	---	1,200	---	2,600	2,650	3,025	3,150	0.412
	GPI 65	---	254	4,900	1,210	1,120	---	1,210	---	2,610	2,700	3,070	3,175	0.412
11-7/8	GPI 40	PRI-40	330	3,990	1,460	1,225	---	1,460	---	2,600	2,750	3,025	3,175	0.515
	GPI 65	---	434	6,325	1,495	1,230	---	1,495	---	2,610	2,800	3,070	3,200	0.515
	GPI 90	PRI-90	661	10,255	1,925	1,400	1,900	1,900	1,925	3,355	3,850	3,850	---	0.515
14	GPI 40	PRI-40	482	4,790	1,715	1,250	---	1,715	---	2,600	2,850	3,025	3,200	0.607
	GPI 65	---	640	7,605	1,740	1,335	---	1,740	---	2,610	2,900	3,070	3,225	0.607
	GPI 90	PRI-90	965	12,235	2,125	1,400	1,900	1,900	2,125	3,355	3,855	3,970	4,250	0.607
16	GPI 40	PRI-40	657	5,550	1,990	1,235	1,350	1,550	1,990	2,600	2,950	3,025	3,225	0.693
	GPI 65	---	877	8,755	2,000	1,345	1,575	1,650	2,000	2,610	3,000	3,070	3,250	0.693
	GPI 90	PRI-90	1,306	14,020	2,330	1,400	1,900	1,900	2,330	3,355	3,855	3,970	4,470	0.693

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 4.448 N

- (a) The tabulated values are design values for normal duration of load. All values, except for EI and C, shall be permitted to be adjusted for other load durations as permitted by the code.
- (b) The maximum vertical load transfer of GPI® Series I-Joists provided in this table is 2,000 plf.
- (c) Bending stiffness (EI) of the I-joist.
- (d) Moment capacity (M) of the I-joist, which shall not be increased by any repetitive member use factor.
- (e) Shear capacity (V) of the I-joist.
- (f) Interpolation of the end reaction between 1-3/4- and 4-inch bearing is permitted.
- (g) Coefficient of shear deflection (C). For calculating uniform load and center-point load deflections of the I-joist in a simple-span application, use Eqs. 1 and 2.

$$\text{Uniform Load: } \delta = \frac{22.5 \omega \ell^4}{EI} + \frac{\omega \ell^2}{C} \quad [1]$$

$$\text{Center-Point Load: } \delta = \frac{36 P \ell^3}{EI} + \frac{2 P \ell}{C} \quad [2]$$

Where:

- δ = calculated deflection (in.),
- ω = uniform load (lbf/ft),
- ℓ = design span (ft),
- P = concentrated load (lbf),
- EI = bending stiffness of the I-joist (lbf-in.²), and
- C = coefficient of shear deflection (lbf-ft/in.).

APA – The Engineered Wood Association is an accredited certification body under ISO 65 by Standards Council of Canada (SCC) and an accredited inspection agency by the International Code Council (ICC) International Accreditation Service (IAS) under ISO/IEC 17020. APA is also an accredited testing organization recognized by IAS and SCC under ISO/IEC 17025. APA is a recognized testing laboratory by Miami-Dade County, and a Product Testing Laboratory, Product Quality Assurance Entity, and Product Validation Entity by the Florida Department of Community Affairs (DCA).

**APA – THE ENGINEERED WOOD ASSOCIATION
HEADQUARTERS**

7011 So. 19th St. ▪ Tacoma, Washington 98466
Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
(253) 620-7400 ▪ E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of *APA – The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility of product performance or designs as actually constructed.